



IN THE CLAIMS

Please cancel Claims ~~1-7~~.

Please add new Claims 8-20 as follows.

B' 8. (New) A thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker.

9. (New) The thermoplastic resin composition of Claim 8, wherein the styrene polymer is an ABS resin.

10. (New) A metalized molded product comprising a molded product made of a thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker and a metal plating provided on the molded product.

11. (New) The metalized molded product of Claim 10, wherein the fibrous filler is carbon fiber.

12. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin composition further comprises a flame retardant.

13. (New) The metalized molded product of Claim 12, wherein the flame retardant is at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

14. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin is at least one member

selected from the group consisting of a polyamide and an ABS resin.

B1  
Cont.  
15. (New) The metalized molded product of Claim 14, wherein the thermoplastic resin is an ABS resin.

16. (New) A thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin comprising at least one member selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) carbon fiber, 5-60% by weight of a whisker having a specific gravity of at least 2 and a flame retardant comprising at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

17. (New) The thermoplastic resin composition of Claim 16, wherein the thermoplastic resin is an ABS resin.

18. (New) The thermoplastic resin composition of Claim 8, additionally comprising a hydrated metal flame retardant.

19. (New) The metalized molded product of Claim 13, wherein the flame retardant is a hydrated metal flame retardant.

20. (New) The thermoplastic resin composition of Claim 16, wherein the flame retardant is a hydrated metal flame retardant.

---